

Carbon Fiber Tape



Overview: Graphite fibers contain up to 95% carbon and yield the highest tensile strength in the FRP industry. These fibers woven together form graphite fabric. These fabrics offer higher strength and stiffness-to-weight ratios than any other commonly available reinforcements. While there are hundreds of types to choose from, we have selected three styles of standard modulus carbon fiber which are suitable for use in racing, aircraft, competition marine, and light industrial applications. To maximize the fiber properties we recommend using only epoxy or vinyl ester resin, although polyesters will bond to the fabrics. Graphite Tapes are ideal for selective reinforcement of graphite fabrications, sleeve winding, lap joining, and repairs of cracks on graphite surfaces. This

product is considered a “tape” because of the narrow width and finished edge. They are in no way adhesive and are meant to be laminated as reinforcement.

Available in 10 yard and 50 yard rolls.

General Properties for Carbon Fiber Fabrics:

- Lightweight
- High Modulus
- High Strength
- Fire Resistant
- Dimensionally Stable
- Fatigue Resistant

Specific Product Properties:

Weave Pattern	Plain
Yarn Description	Warp: 3K Multifilament Cont. Tow
	Fill: 3K Multifilament Cont. Tow
Count (Ends x Picks) inches	12.5 x 12.5
Weight	5.7 oz/yard ²
Thickness	0.012 inches

Weave Pattern Rankings:

	Thickness	Weight	Strength	Porosity
Plain	3	1	3	1
Twill	2	1	4	2
4-Harness Satin	3	1	4	2
8-Harness Satin	1	1	7	4
Leno	7	7	1	7
Mock Leno	6	1	2	4

This was a scale from 1 to 7, with 1 being the lowest and 7 being the highest.

Information presented herein has been compiled from sources considered to be dependable and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so. Nothing herein is to be construed as recommending any practice or any product violation of any patent or in violation of any law or regulation. It is the user's responsibility to determine for himself the suitability of any material for a specific purpose and to adopt such safety precautions as may be necessary. We make no warranty as to the results to be obtained in using any material and, since conditions of use are not under our control, we must necessarily disclaim all liability with respect to the use of any material supplied by us.

Resin Compatibility

Part Number	Polyester Resin	Vinyl Ester Resin	System 2000 Epoxy
292	X	X	P
530	X	X	P
596	X	X	P
597	X	X	P
598	X	X	P
660	X	X	P
1064	X	X	P
1069	X	X	P

A "P" is for the primary resin for the fabric.
An "X" means the fabric is compatible with the resin.
The compatibility is based on Fibre Glast Development's resins only